

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 08-231655

(43)Date of publication of application : 10.09.1996

(51)Int.Cl. C08F290/06
C09D 4/02
C09D 5/08
C09D175/14

(21)Application number : 07-040520 (71)Applicant : DAINIPPON INK & CHEM INC

(22)Date of filing : 28.02.1995 (72)Inventor : YASUMURA TAKASHI
FUKAKUSA KUMIKO
MITANI TOMOMASA

(54) RESIN COMPOSITION, LINING AGENT AND MOLDING MATERIAL

(57)Abstract:

PURPOSE: To provide a resin compsn. which is excellent in surface drying property (cold setting property), water resistance, storage stability, foldability, and adhesion and has long-term stability of properties such as tensile strength and elongation.

CONSTITUTION: This compsn. comprises a polyether-urethane acrylate resin (A) having (meth)acryloyl and allyl ether groups and a polymerizable unsaturated monomer (B) wherein the urethane (meth)acrylate resin has an allyl ether group concn. of 0.1 to less than 1.0mmol/g and a (meth)acryloyl group concn. of 0.2 to 2.0mmol/g with the concn. ratio of the (meth)acryloyl group to the allyl ether group being 1.2 to 10.

LEGAL STATUS

[Date of request for examination] 13.12.2001

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against examiner's
decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2000 Japan Patent Office